PAT-NO:

JP402048422A

DOCUMENT-IDENTIFIER: JP 02048422 A

TITLE:

STIRRING ROD FOR GLASS INDUSTRY

PUBN/DATE:

February 19, 1990

INVENTOR-INFORMATION:

NAME

COUNTRY

MURAKISHI, YUKIHIRO NOMURA, TADASHI

ASSIGNEE-INFORMATION:

NAME

COUNTRY

TANAKA KIKINZOKU KOGYO KK N/A

APPL-NO:

.IP63198465

APPL-DATE: August 9, 1988

INT-CL (IPC): C03B005/187

US-CL-CURRENT: 65/178, 65/356, 65/374.12

ABSTRACT:

PURPOSE: To prevent the dissolution and melting damage of platinum (alloy) and to improve the durability by using a hollow stirring rod for glass industry made of platinum (alloy) at least at the outer surface contacting with glass and introducing a cooling gas into the hollow part of the rod.

CONSTITUTION: A stirring rod 4 for glass industry is composed of a support 1 made of a platinum or a platinum alloy at least at the outer surface contacting with glass, a spiral blade 2 attached to the outer circumference of the lower part of the support 1 and a U-shaped blade 3 perpendicularly attached to the support 3 at a part above the spiral blade. The support 1 and the blade 3 of the stirring rod 4 have hollow structure and the hollow parts of the support 1 and of the blade 3 are connected with each other via a through- hole 5. A pipe 6 for blasting cooling gas is inserted into the support 1. A cooling gas is introduced from a cooling gas source through a blasting tube 6 into the support 1 and the blade 3 to lower the outer surface temperature of the stirring rod 4. The glass contacting with the outer surface of the rod is solidified in the form of a thin film during stirring to protect the outer surface of the stirring rod 4.

COPYRIGHT: (C)1990,JPO&Japio

Abstract Text - FPAR (2):

CONSTITUTION: A stirring rod 4 for glass industry is composed of a support 1 made of a platinum or a platinum alloy at least at the outer surface contacting with glass, a spiral blade 2 attached to the outer circumference of the lower part of the support 1 and a U-shaped blade 3 perpendicularly attached to the support 3 at a part above the spiral blade. The support 1 and the blade 3 of the stirring rod 4 have hollow structure and the hollow parts of the support 1 and of the blade 3 are connected with each other via a through-hole 5. A pipe 6 for blasting cooling gas is inserted into the support 1. A cooling gas is introduced from a cooling gas source through a blasting tube 6 into the support 1 and the blade 3 to lower the outer surface temperature of the stirring rod 4. The glass contacting with the outer surface of the rod is solidified in the form of a thin film during stirring to protect the outer surface of the stirring rod 4.

Current US Cross Reference Classification - CCXR (1):

65/178

£

(9 日本国特許庁(IP)

⑩ 特許出願公開

◎ 公開特許公報(A) 平2-48422

@Int. Cl. 5

識別記号 庁内整理番号 総公開 平成2年(1990)2月19日

C 03 B 5/187

6359-4G

審査請求 未請求 請求項の数 1 (全2頁)

69発明の名称 ガラス窯業用撹拌棒

> ②特 顧 昭63-198465

29出 顧 昭63(1988) 8月9日

70発 明 者 村 崖 #

神奈川県伊勢原市鈴川26番地 田中貴金属工業株式会社伊 勢原工場内

70発明

īF

神奈川県伊勢原市鈴川26番地 田中貴金属工業株式会社伊 **勢原丁場内**

の出 願 田中貴金属工業株式会 東京都中央区日本橋茅場町2丁日6番6号

社

明

1. 発明の名称

ガラス窯業用機拌機

2. 特許請求の範囲

1. 支柱と該支柱に取付られた環とより成り、 それの少なくともガラスと接触する外表面が白金 又は白金合金で形成されたガラス窯業用撹拌棒に 於いて、該撹拌棒を中空になし、その撹拌棒内に 冷却用ガスを吹き込むようにしたことを特徴とす るガラス窓業用機枠棒。

3. 発明の詳細な説明

(産業上の利用分野)

本発明は、ガラス窯業用撹拌棒の改良に関する。 (従来の技術)

従来、ガラス溶解時、約1200℃の高温ガラスを 搅拌する為に、耐火物その他の耐熱性材料より成 る芯材を白金又は白金合金で被い、その上に白金 又は白金合金から成る例えば螺旋状の翼を取付け た撹拌棒を使用していた。

(発明が解決しようとする課題)

ところで、高温溶解ガラスの熱影響により白金 又は白金合金が溶融ガラス中に溶出する為、溶解 ガラスが汚染され、ガラスの特性、品質が劣化し た。また白金又は白金合金が溶損し、亀裂が生じ て、短期間の内に使用不能となっていた。

(発明の目的)

本発明は上記課題を解決すべくなされたもので、 搅拌棒の外表面の白金又は白金合金が容出、溶損 しないようにしたガラス窯業用撹拌棒を提供する ことを目的とするものである。

(課題を解決するための手段)

上記課題を解決するための本発明のガラス窯菜 用撹拌棒は、支柱と該支柱に取付けられた翼とよ り成り、それの少なくともガラスと接触する外表 面が白金又は白金合金で形成されたガラス窯業用 撹拌棒に於いて、該撹拌棒を中空となし、その撹 拌棒内に冷却用ガスを吹き込むようにしたことを 特徴とするものである。

(作用)

本発明のガラス窯業用撹拌棒は上述の如く構成

特開平2-48422(2)

されているので、ガラス溶解中機拌線内に空気又はN₂ガス、Arガス等の不活性ガスを吹き込み、 機拌棒の白金又は白金合金の外表面温度を下げる ことにより、機拌時接触する溶融ガラスが薄膜状 に固化するので、白金又は白金合金の外表面が保 護されて溶出、溶損が防止される。

(実施例)

وه . خو


4. 図面の簡単な説明

図は本発明のガラス窯業用撹拌棒の一実施例を 示す維斯面図である。

出願人 田中增金属工業株式会社

このように構成された実施例のガラス窯業用撹拌棒 4 をガラス溶解るつぼ内にセットし、1200ででの光学ガラスの溶解に於いて、因示せぬ N 2 ガスの供給源より支柱 1 及びコ字型の翼 3 内に N 2 ガスを吹き込み、撹拌棒 4 の外表面の温度を下げることにより、撹拌時外表面に接触する溶融がラスは薄膜状に固化するので、撹拌棒 4 の外表面が保護されて、白金ロジウム合金の溶出、溶復が防止される。

(発明の効果)



1 ... 方村

2… 螺旋状の翼 3… コ字型の翼

4… 撹拌棒

5… 透孔

6 … 冷却用ガス吹込み管